

Country Chic Paint Ltd
209-225 Canada Ave
V9L 1T6 Duncan BC
CANADA

Eurofins Product Testing A/S
Smedeskovvej 38
8464 Galten
Denmark

VOC@eurofins.com
www.eurofins.com/VOC-testing

VOC TEST REPORT

VOC Content

21 September 2017

1 Sample Information

Sample name	Country Chic Paint - Glaze
Sample no.	392-2017-00298803
Production date	
Batch No.	
Sample reception	04/09/2017



Morten Sielemann
Analytical Chemist

2 Applied Test Methods

2.1 General Test References

Test	Regulation, protocol or standard	Version	Internal SOP	Limit of detection [g/L]	Uncertainty Um \pm
VOC	ISO 11890-2	2013	71 M 546002	1	20%
VOC	ASTM D6886	2014	71 M 546002	1	20%

3 Results

3.1 Results Used in Calculation

	Remarks on the test results	Results	Unit
Density	Supplied by the Customer	1.098	g/mL

3.2 Total VOC Content

	CAS No.	Results	Unit
Butyldiglycol	112-34-5	1.8	g/L
VOC content	-	1.8	g/L

4 Appendices

4.1 How to Understand the Results

4.1.1 Acronyms Used in the Report

- < Means less than
- > Means bigger than
- * Not a part of our accreditation
- ⌘ Please see section regarding uncertainty in the Appendices.
- 1 Analysed by another Eurofins laboratory

4.2 Description of VOC/SVOC Content Test

4.2.1 Testing of VOC and SVOC

Volatile Organic Compounds (VOC) include all organic compounds with an initial boiling point less than or equal to 250 °C measured at standard pressure of 101.3 kPa.

The determination is performed in conformity with ISO 11890-2 and the commission decision 2014/312/EU of 28 May 2014 establishing the ecological criteria for the award of the EU Ecolabel for indoor and outdoor paints and varnishes, with its most recent amendments and its most recent User Manual.

Analyses are performed with a slightly polar gas chromatographic column (HP-5). Mass spectrometric detection is used for identification and flame ionization detector is used for quantification. Identified compounds are quantified with their authentic response factors, or with their relative response factors using 1,2-diethoxyethane as internal standard. Remaining unknown peaks are quantified in diethyl adipate equivalents.

4.3 Uncertainty of the Test Method

The relative standard deviation of the overall analysis is 10%. The expanded uncertainty U_m equals 2 x RSD. For further information please visit www.eurofins.dk/uncertainty.